Sales Data Sheet

Version 1 from 2026/04/20

00518.99

NAME

XO FLAX PURE 130

DESCRIPTION

Spunlace 65% Flax 35% VIS flat (FL) Color Nature

TYPE	COMPOSITION	SURFACE
Spunlace	**65% Flax 35% VIS**	**flat**

Fire Rating (applied to the wall)*	EN 13501:2007	B-s1,d0	
	ASTM E84	A-rating	
CE Certification	EN 15102:2007+A1:2011	CE	
COV Emission	DIN ISO 16000-3/-6/-9/-11	A+	
Sound Absorbtion Rate	DIN EN ISO 10534	0,07	Applied to the wall
	DIN EN ISO 354:2003	0,67	20 mm distance to the wall
Printing Profiles	Canon Colorado	UVgel certified	
	HP Latex	Profiled only	

PROPERTY	DIRECTION	TEST METHOD	UNITS	VALUES
Weight		DIN EN 29073-1 / ISO 9073-1	g/m²	130
Thickness		DIN EN 29073-2 / ISO 9073-2	mm	0,71
Tensile strength	MD	DIN EN 29073-3 / ISO 9073-3	N/5 cm	> 140
	CD		N/5 cm	> 110
Elongation at break	MD	DIN EN 29073-3 / ISO 9073-3	%	< 35
	CD		%	< 50
Air permeability @ 200 Pa		DIN EN ISO 9237	l/dm²/min	500

* FR-Version for other application available as item 01784.99

Disclaimer: The data are based on the determination and measurements of virgin fabrics and are subject to usual tolerances. This information does not express or imply any guarantee and the right is reserved to make any alterations without notice.

Please get in touch for specific finishing! Our products can be enhanced with a textile backing, surface coating, self-adhesive function or a print primer.

OEKO TEX® STANDARD 100 16.0.90034 Hohenstein HTTI www.oeko-tex.com

ÉMISSIONS DANS L'AIR INTÉRIEUR A+

Norafin Industries (Germany) GmbH
Gewerbegebiet Nord 3 | 09456 Mildenau
Tel. +49 3733 5507 0
info@norafin.com
www.norafin.de