

Sales Data Sheet

Version 1 from 2026/04/20

03160.99

NAME

XO LYOCELL PURE 140

DESCRIPTION

Spunlace 100% Lyocell flat (FL) Color White

Norafin 

 **EXTRA[®]
ORGANIC**
A Brand of Norafin

TYPE

Spunlace

COMPOSITION

100% Lyocell

SURFACE

flat

Fire Rating

(applied to the wall)*

ASTM E84

A-Rating

CE Certification

EN 15102:2007+A1:2011



Sound Absorbtion Rate

DIN EN ISO 10534
DIN EN ISO 354:2003

Applied to the wall
20 mm distance to the wall

Printing Profiles

Canon Colorado
HP Latex

UVgel certified
Profiled only

PROPERTY	DIRECTION	TEST METHOD	UNITS	VALUES
Weight		DIN EN 29073-1 / ISO 9073-1	g/m ²	140
Thickness		DIN EN 29073-2 / ISO 9073-2	mm	0,85
Tensile strength	MD	DIN EN 29073-3 / ISO 9073-3	N/5 cm	> 235
	CD		N/5 cm	> 160
Elongation at break	MD	DIN EN 29073-3 / ISO 9073-3	%	< 30
	CD		%	< 55
Air permeability @ 200 Pa		DIN EN ISO 9237	l/dm ² /min	> 500

* FR-Version for other application available as item 01784.99

Disclaimer: The data are based on the determination and measurements of virgin fabrics and are subject to usual tolerances. This information does not express or imply any guarantee and the right is reserved to make any alterations without notice.

Please get in touch for specific finishing! Our products can be enhanced with a textile backing, surface coating, self-adhesive function or a print primer.



STANDARD
100

16.0.90034
Hohenstein HTTI

www.oeko-tex.com

Norafin Industries (Germany) GmbH
Gewerbegebiet Nord 3 | 09456 Mildena
Tel. +49 3733 5507 0
info@norafin.com
www.norafin.de